

Amendments to the Claims:

This listing of claims will replace all prior listings of claims in the application:

1. (Currently Amended) An acrylic release agent precursor which contains a poly(meth)acrylate ester having a group capable of being activated by ultraviolet radiation and has a storage elastic modulus of 1×10^2 to 3×10^6 Pa at 20°C and a frequency of 1 Hz, wherein said precursor, after irradiation with ultraviolet radiation, has a contact angle of 15° or more to a mixed solution of methanol and water (~~volume ratio of 90/10~~) **at a volume ratio of 90/10 and** having a wetting tension of 25.4 N/m.
2. (Original) The acrylic release agent precursor according to claim 1, wherein the poly(meth)acrylate ester has a group capable of being activated by ultraviolet radiation derived from benzophenone.
3. (Original) The acrylic release agent precursor according to claim 1, wherein the poly(meth)acrylate ester is derived from a monomer component containing
 - a first alkyl (meth)acrylate having a C₁₂₋₃₀ alkyl group,
 - a second alkyl (meth)acrylate having a C₁₋₁₂ alkyl group, and
 - a (meth)acrylate ester having a group capable of being activated by ultraviolet radiation.
4. (Original) The acrylic release agent precursor according to claim 1, wherein the poly(meth)acrylate ester is derived from a monomer component containing
 - an alkyl (meth)acrylate having a branched C₈₋₃₀ alkyl group, and
 - a (meth)acrylate ester having a group capable of being activated by ultraviolet radiation.
5. Cancelled

6. (Currently Amended) A process for producing an acrylic release agent article, which comprises the steps of:

coating a substrate with an acrylic release agent precursor which contains a poly(meth)acrylate ester having a group capable of being activated by ultra violet radiation and has a storage elastic modulus of 1×10^2 to 3×10^6 Pa at 20°C and a frequency of 1 Hz, and

irradiating the acrylic release agent precursor with ultraviolet radiation to form an acrylic release agent layer having a contact angle of 15° or more to a mixed solution of methanol and water (~~volume ratio of 90/10~~) **at a volume ratio of 90/10 and** having a wetting tension of 25.4 N/m.

7. (Previously Presented) A release agent article comprising a substrate and the release agent precursor of claim 1 formed on the substrate, wherein the release agent precursor has been irradiated with ultraviolet radiation.

8. (Previously Presented) The release agent article of claim 7, wherein the poly(meth)acrylate ester has a group capable of being activated by ultraviolet radiation derived from benzophenone.

9. (Previously Presented) The release agent article of claim 7, wherein the poly(meth)acrylate ester is derived from a monomer component containing
a first alkyl (meth)acrylate having a C₁₂₋₃₀ alkyl group,
a second alkyl (meth)acrylate having a C₁₋₁₂ alkyl group, and
a (meth)acrylate ester having a group capable of being activated by ultraviolet radiation.

10. (Previously Presented) The release agent article of claim 7, wherein the poly(meth)acrylate ester is derived from a monomer component containing
an alkyl (meth)acrylate having a branched C₈₋₃₀ alkyl group, and
a (meth)acrylate ester having a group capable of being activated by ultraviolet radiation.